



GLOBAL GREEN MATERIAL

PCR PP 3PA-W00-F

TECHNICAL DATA SHEET

Version 1.1	01/01/2024
-------------	------------

GENERAL PRINCIPLE

Recycled plastic source stream	Unpigmented post-consumer recycled PP cups and food containers sourced in Taiwan. (100% PCR PP)
--------------------------------	---

RESIN

Pellets	PP	3PA-W00-F (PCR/food grade, color sorted)
---------	----	--

REGULATORY VALIDATION

PARAMETERS	SPECIFICATIONS
------------	----------------

The US FDA's regulation of recycled plastics for food-contact applications	PNC No. 2999 November 2, 2023
--	-------------------------------

Material Safety Test reference to F.D.A. Regulation U.S. 21 CFR Part 177.1520 Clauses (c)(1.1) And (d)	PASS Be reported on Intertek (No. TWNC01200506S1) Sep 01, 2023
---	---

Global Automotive Declarable Substance List (GADSL)	PASS Be reported on GUANGZHOU CUSTOMS DISTRICT TECHNOLOGY CENTER (No. FCM2022030301176-2) 2022
---	---

Global Recycled Standard (GRS) Version 4.0	Scope Certificate Number:CU1166343GRS-2023-00098424
--	---

RoHS 2011/65/EU Reference to RoHS 2011/65/EU Annex II and amending Directive EU 2015/863	PASS Be reported on Intertek (No. TWNC01200500S1) Sep 01, 2023
---	---

As per article 33(1) to regulation (EC) NO. 1907/2006(REACH)	PASS Be reported on Intertek (No. TWNC01200503S1) Sep 01, 2023
--	---

MATERIAL CHARACTERISTICS

PROPERTY	SPECIFICATIONS	METHODS
Melt Index	4.5 ±2.0g/10min 230°C,2.16kg	ASTM D1238
Density	0.910±0.020 g/cm ³	ASTM D792
Tensile Strength	29.4±6 MPa	ASTM D638

	310±50 Kg/cm ²	
Max Elongation	≥ 150 %	ASTM D638
Flexural Strength	48.1±10 MPa	ASTM D790
	460±50 Kg/cm ²	
Flexural Modulus	1100±150 MPa	ASTM D790
	11800±1000Kg/cm ²	
Izod Impact	>50 J/m	ASTM D256
% Polyethylene	Max 5%	FTIR
Moisture	≤ 0.3%	105 °C 30 min
Heat Deflection Temperature	98°C	ASTM D648
QUALITY		
Pellet Size	4 mm diameter	
Filtration (Screen pack)	120 mesh(125 um)*2	
Package	<input type="checkbox"/> Ton sack <input type="checkbox"/> 25Kg/pcs	
Impurities	<p>∅ >0.5mm : no more than 4 impurities ∅ =0.12-0.5mm : no more than 10 impurities ∅ <0.12mm:pass Checking from 5cm diameter and 3.3mm thickness circle testing chip(one side)</p>	
Expiration	One year after production	
Storage	Store in a cool, dry place with adequate ventilation. Keep away from incompatible materials, open flames, and high temperatures.	